

FIRE RATINGS

Early Fire Hazard Indices Test Results

S06

Due to the demand within the industry, we have tested the following on a wide range of differing substrates, also over existing paint and polyurethane.

ALL TESTS TO AS 1530:3-1982

	Ignitability	Spread of Flame	Heat Evolved	Smoke Developed System	
Flame Control 9.5mm Particle Board	0	0	0	5	(1)
Flame Control 19mm Particle Board	0	0	0	5	(1)
Flame Control Existing Varnished Particle Board	0	0	0	5	(1)
Muralflex High Build 9.5mm Gib Board	11	0	3	3	(4)
Flame Control Solid Timber Walls (Modulock homes) (sealer required)	0	0	0	5	(1)
Modocryl High Build 9mm Fibro Cement Panel	0	0	0	2	(4)
Protective Paints 9.5mm Gib Board	0	0	0	3	(2)
Silcabond SP 10mm Fibre Cement Panel	0	0	0	2	(3)
Silcabond SP 20mm Particle Board	13	2	0	6	(6)

For further technical information contact Protective Paints Ltd on 0800 724 684